Ketley Classic and Tenger Staffordshire Clay Pavers

Specification Sheet



Performance Standard: BS EN 1344:2013

Ketley Staffordshire Pavers are produced at our works located in the heart of the Black Country. They have been made from our own Etruria Marl since Victorian times. Their unrivalled physical properties include their strength, durability and permanence of colour.

| Work Size mm | Pattern | Pack Weight | No per pallet | Units/m² Rigid with 10mm joint | Units/m ² Flexible butt jointed (3mm joint) |
|---------------------------------|--------------|-------------|--|--------------------------------------|--|
| 215x102.5x50 | Square Edged | 1300kg | 500 | 40 | 44 |
| 215x102.5x65 | Square Edged | 1320kg | 400 | 40 | 44 |
| 200x100x50 | Square Edged | 1150kg | 500 | 43 | 48 |
| 200x100x65 | Square Edged | 1200kg | 400 | 43 | 48 |
| 200x100x50 | Chamfered | 1150kg | 500 | 43 | 48 |
| 200x100x65 | Chamfered | 1200kg | 400 | 43 | 48 |
| 200 x50x65 | Square Edged | 1024kg | 640 | 80 | 93 |
| Colour | | | Staffordshire Blue, Staffordshire Brown Brindle, Staffordshire Red, Brown Antique | | |
| Raw Material | | | Etruria Marl Clay | | |
| Manufacture | | | Extruded, Wirecut and fired above 1130°C | | |
| Bulk Density | | | 2,300kg/m ³ | | |
| Texture | | | Dragfaced | | |
| Size, Tolerance | | | BS EN 1344: 2013 | | |
| Size Range | | | R1 | | |
| Mean Transverse Breaking Load | | | T4 | | |
| Unpolished Slip/Skid Resistance | | | U3 | | |
| Abrasion Resistance | | | A3 | | |
| Freeze/Thaw Resistance | | | FP100 | | |

Ketley Brick Company Ltd

Dreadnought Works, Pensnett, Brierley Hill, West Midlands, DY5 4TH, UK
Tel: 01384 78361 Fax: 01384 74553 Email: info@ketley-brick.co.uk Web: www.ketley-brick.co.uk
Ketley Brick Company Ltd. is a company registered in England and Wales with Reg number 699040.